

塑美达™ ESD C 200 A

Nylon 6 (PA)

ESD Protection

Electrically Conductive

General常规

Material Status材料状况	• Commercial: Active	
Availability	有效性	• CHINA
Primary Additive主添加剂		
Uses 用途	• Automotive Electronics • 汽车电子 • Automotive Under the Hood • 汽车引擎盖室 • Cell Phones手机 • Electrical/Electronic Applications 电子/电器应用 • General Purpose通用 • Housings住宅 • Industrial Applications工业用途 • Machine/Mechanical Parts机器零件 • Metal Replacement金属替代 • Power/Other Tools动力/其他工具 • Thick-walled Parts •厚壁零件 • Valves/Valve Parts •阀门/阀门零件 • Gear/Sliding parts•齿轮/滑动件 • Connector•连接器/接插件	

RoHS Compliance RoHS标准	• RoHS Compliant 符合		
Appearance外观	• Black黑色	• Natural Color自然色	
Forms形态	• Pellets颗粒		
Processing Method加工方式	• Injection Molding 注塑		
Physical物理性能	Dry干态	Conditioned	Unit Test method标准
Density 密度/ Specific Gravity比重			
--	1.19	--	ASTM D792
--	1.19	-- g/cm³	ISO 1183/A
Molding Shrinkage成型收缩率			ASTM D955
Flow流动方向	1.40 - 1.80	-- %	
Across Flow垂直流动方向		%	
Water Absorption 吸水率¹ (24 hr, 23°C)		-- %	ASTM D570
Mechanical机械性能	Dry	Conditioned	Unit Test method
Tensile Modulus拉伸模量	2845		MPa ASTM D638
Tensile Strength (Break)拉伸强度（断裂）	54		MPa ASTM D638
Tensile Elongation (Break)拉伸断裂伸长率	8.0 - 12.0		% ASTM D638
Flexural Strength弯曲强度	89		MPa ASTM D790
Flexural Modulus弯曲模量	2705		MPa ASTM D790
Impact冲击性能	Dry	Conditioned	Unit Test method
Notched Izod Impact缺口冲击强度	106		J/m ASTM D256
Unnotched Izod Impact无缺口冲击强度	No break		J/m ASTM D256
Thermal热性能	Dry	Conditioned	Unit Test method
Deflection Temperature Under Load			
0.45 MPa, Annealed, 3.18 mm			°C ASTM D648
1.82 MPa, Annealed, 3.18 mm			°C ASTM D648
Flame Rating ² (1.6 mm)防火			UL 94
Electrical电性能	Dry	Conditioned	Unit Test method
Volume Resistivity体积电阻	< 1E3		ohm.cm ASTM D 257
Surface Resistivity表面电阻	< 1E6		ohm.cm ASTM D 257
Dielectric strength介电强度			kV/mm ASTM D149
Dielectric constant介电常数			(1 MHz) ASTM D150
Dielectric loss介电损耗			(1 MHz) ASTM D150
Injection注塑工艺	Dry Unit		
Drying Temperature干燥温度	82 °C		
Drying Time干燥时间	2 hrs		
Suggested Max Moisture建议最大含水率			
Processing (Melt) Temp熔体温度	243 - 279 °C		
Mold temperature 模具温度	54 - 93 °C		
Injection pressure注塑压力	65 - 100 MPa		

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results. Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.